


BOSTRAIL[®] Traction Power Cable

single conductor / EPR insulated / XLPO jacket / 4/0 AWG to 2000 KCMIL / 2000 volt



Applications

These are single conductor 2000 volt power cables where low-smoke non-halogen cables are required. They consist of a ethylene propylene rubber insulated conductor jacketed with a tough low smoke zero halogen (LSZH) crosslinked polyolefin (XLPO) jacket. They are highly heat, oil and moisture-resistant, extremely tough yet flexible, and can sustain 90°C wet or dry operating temperatures. A shielded version is available as well.

Ratings

- Rated 90°C Wet or Dry Traction Power Cable
- UL 1581 Vertical Tray (70,000 BTU)
- UL RHW-2

Construction

CONDUCTOR: The conductor is class “B” stranded compressed concentric round in accordance with ASTM B8. The wires are uncoated soft, annealed copper of 100% conductivity in accordance with ASTM B3. The conductor resistance meets the requirements of ICEA S-95-658 (NEMA WC70).

INSULATION: Low smoke non-halogen ethylene propylene rubber (EPR) rated for 90°C wet or dry, complying with ICEA standards (see chart on back). The insulation fits tightly to the conductor but is ‘clean-stripping.’ An opaque polyester tape or other suitable separator is used over the conductor.

JACKET: Flame retardant, low smoke non-halogen and oil resistant crosslinked polyolefin (XLPO) jacket (see chart on back). The jacket is bonded to the EPR insulation.

Prysmian Group

700 Industrial Drive | Lexington, SC 29072 | +1-800-845-8507 | www.prysmiangroup.com

Sales and Distribution:

22 Joseph E. Warner Blvd. | North Dighton, MA 02764 | +1-508-822-5444
One Tamaqua Blvd. | Schuylkill Haven PA 17972 | Tel +1-570-385-4381

BOSTRAIL® Traction Power Cable

single conductor / EPR insulated / XLPO jacket / 4/0 AWG to 2000 KCMIL / 2000 volt

Part Number	Conductor Size	Stranding	Average Insulation Thickness in (mm)	Average Jacket Thickness in (mm)	Minimum Bend Radius in (cm)	Ampacity* 90°C	Cable O.D in (mm)	Approximate Cable Weight Lbs/Mft (Kg/Km)
TR0000	4/0 AWG	19/W	.110 (2.8)	.065 (1.7)	3.5 (89)	405	0.880 (22.3)	900 (1341)
TR0500	500 KCMIL	37/W	.110 (2.8)	.080 (2.0)	5.0 (127)	700	1.190 (30.2)	1930 (2875)
TR0750	750 KCMIL	61/W	.125 (3.2)	.080 (2.0)	6.0 (152)	885	1.400 (35.6)	2870 (4276)
TR1000	1000 KCMIL	61/W	.125 (3.2)	.095 (2.4)	6.5 (165)	1055	1.580 (40.1)	3710 (5528)
TR1500	1500 KCMIL	91/W	.125 (3.2)	.095 (2.4)	7.5 (191)	1325	1.830 (46.5)	5380 (8016)
TR2000	2000 KCMIL	127/W	.125 (3.2)	.110 (2.8)	8.5 (216)	1725	2.080 (52.8)	7100 (10579)

*Ampacity based on ambient air temperature of 30°C in free air

*Representative spec - Draka manufactures to all transit and railroad specifications accordingly.

The data herein is approximate and subject to normal manufacturing tolerances.

Information is subject to change without notice. Consult factory for a variety of alternate constructions for specific applications.

Requirements for EPR Insulation

Characteristics	Test Method	Guaranteed Values
Tensile Strength, PSI	ASTM D470	1200 min
Elongation, %	ASTM D470	150 min
Air Oven Aging (7 days @ 121°C)		ASTM D573
Tensile Strength, %		75 min
Elongation, %		75 min
Air Oven Aging (7 days @ 150°C)		ASTM D573
Tensile Strength, %		75 min
Elongation, %		75 min
Gravimetric Water		ASTM D470
Absorption, 7 days @ 70°C, mg/in ²		
Water Absorption (EM-60)		ASTM D470
Electrical Method @ 75°C		
Specific Conductive Capacitance (SIC)		3.5 max
Capacitance Increase (1 - 14 days immersion, %)		2.0 max
Capacitance Increase (7 - 14 days immersion, %)		1.0 max
Stability Factor (after 14 days immersion, %)		1.0 max
Insulation Resistance Constant (K), Megohms-1000 ft	ICEA 95-658	20,000 min

Requirements for Insulation and Jacket

Characteristics	Test Method	Guaranteed Values
Halogen Content, %	MIL-C-24643	0.2 max
Ozone Resistance (150 ppm @ 25°C)		pass
Smoke Index	NES 711	25 max
Smoke Density (100 mil slab)		ASTM E662
Flaming Mode Ds 4 Min		50
Flaming Mode Dm Within 4 Min		250
Non-Flaming Mode Ds 4 Min		50
Non-Flaming Mode Dm Within 4 Min		250
Toxicity Index	NES 711	1.5 max
Acid Gas, % (hydrogen ions)	MIL-C-24643	1.0 max

Requirements for XLPO Jacket

Characteristics	Test Method	Guaranteed Values
Tensile Strength, PSI	ASTM D470	1700 min
Elongation, %	ASTM D470	150 min
Air Oven Aging (7 days @ 121°C)		ASTM D573
Tensile Strength, %		90 min
Elongation, %		75 min
Air Oven Aging (7 days @ 150°C)		ASTM D573
Tensile Strength, %		90 min
Elongation, %		75 min
Oil Immersion Aging (18 hrs @ 121°C)		ASTM D471
Tensile Strength, %		60 min
Elongation, %		60 min
Gravimetric Water		ASTM D470
Absorption, 7 days @ 70°C, mg/in ²		20 max
Durometer, Shore A	ASTM D2240	90 +5
Tear Strength, lbs/in	ASTM D624	35 min
Oxygen Index, %	ASTM D2863	35 min

Requirements for Completed Cable

Characteristics	Test Method	Guaranteed Values
Cold Bend @ -40°C, 24 hrs (8x OD)		pass
IEEE 383 Flame Test		pass

© DRAKA - A Brand of The Prysmian Group. 2012 All Rights Reserved. The information contained within this document must not be copied, reprinted or reproduced in any form, either wholly or in part, without the written consent of Prysmian Group. The information is believed correct at the time of issue. Prysmian Group reserves the right to amend any specifications without notice. These specifications are not contractually valid unless authorized by Prysmian Group. Issued June 2012.

Prysmian Group

700 Industrial Drive | Lexington, SC 29072 | +1-800-845-8507

Sales and Distribution:

22 Joseph E. Warner Blvd. | North Dighton, MA 02764 | +1-508-822-5444 | www.drakausa.com

One Tamaqua Blvd. | Schuylkill Haven PA 17972 | Tel +1-570-385-4381